

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 285 993 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
26.02.2003 Bulletin 2003/09

(51) Int Cl.7: **D21H 21/18, D21H 17/42,
D21H 17/44**

(21) Application number: **02017318.3**

(22) Date of filing: **01.08.2002**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SK TR**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **20.08.2001 US 933408**

(71) Applicant: **Armstrong World Industries, Inc.
Lancaster Pennsylvania 17603 (US)**

(72) Inventors:
• **Kehrer, Kenneth P.
Lancaster PA 17603 (US)**

• **Atlas, Sheldon M.
New York NY 10024 (US)**
• **Kabanov, Victor Alexandrovich
117296 Moscow (RU)**
• **Zezin, Alexander Borisovich
115184 Moscow (RU)**
• **Rogachova, Valentine Borisovna
117311 Moscow (RU)**


(74) Representative: **Finck, Dieter, Dr.Ing. et al
v. Fünér Ebbinghaus Finck Hano
Mariahilfplatz 2 - 3
81541 München (DE)**

(54) Fibrous sheet binders

(57) A method and composition are disclosed for providing a two-part polymer binder additive for a fibrous sheet for improving both its strength and durability. The two-part polymer binder may be added to augment organic binders to increase board strength and durability

or to reduce the amount of organic binder required. The polymers may also be added in place of conventional organic binders or added in addition to organic binders to improve sag resistance and fibrous sheet performance.

Figure 2.
IPEC plus Cross-linking and Binder
Wet and Dry Strength
Functional groups attach to binder at elevated temperature..



EP 1 285 993 A1

Description**FIELD OF INVENTION**

- 5 **[0001]** The present invention generally relates to fibrous sheets and more specifically to polymer additives for enhanced fibrous sheets.

BACKGROUND

- 10 **[0002]** Fibrous sheets are used for a variety of different purposes and are comprised of an array of different fibers, binders and fillers. For example, fibrous sheets can be used as acoustical ceiling tiles, paper products and furniture board. Primarily, fibrous sheets can be comprised of mineral wool, perlite, cellulosic fibers, fillers and binders.
- 15 **[0003]** Fibrous sheet production utilizes combinations of fibers, fillers, bulking agents, binders, water, surfactants and other additives mixed into a slurry and processed into a fibrous sheet. Examples of fibers used may include mineral fiber, fiberglass, and cellulosic material. Mineral wool is a lightweight, vitreous, silica-based material spun into a fibrous structure similar to fiberglass. Cellulosic material is typically in the form of newsprint. Added fillers may include expanded perlite, brighteners such as titanium oxide and clay. Expanded perlite reduces material density and clay enhances fire resistance. Examples of binders used in fibrous sheets include starch, latex and reconstituted paper products, which link together and create a binding system locking all ingredients into a structural matrix.
- 20 **[0004]** Organic binders, such as starch, are often the primary component providing structural adhesion for the fibrous sheet. Starch is often the preferred organic binder because it is relatively inexpensive. For example, fibrous sheets containing newsprint, mineral wool and perlite are often bound together by starch. Starch imparts both strength and durability to the fibrous sheet structure.
- 25 **[0005]** Unfortunately, there is a limit on how much starch can be added before such properties begin to decline. Starch is highly water-soluble and when partially hydrated loses a portion of its ability to bind the fibrous sheet components. Additionally, water-felted and cast panels tend to exhibit limited stability under high moisture loads given the hydrophilic nature of the cellulosic fibers. Furthermore, fibrous sheet strength and durability cannot simply be enhanced by using increased quantities of starch and cellulose, since starch increases a fibrous sheet's susceptibility to moisture and sag.
- 30 **[0006]** Thus, a high degree of starch and cellulose can lead to sagging and weakening of the board under humid conditions. Also, fibrous sheets having large quantities of starch require elevated drying rates or increased drying time to remove excess water from the board. Therefore, there is a need for a method for increasing both the strength and durability of a fibrous sheet without the addition of increased quantities of starch. Additionally, there is a need for a fibrous sheet that is not susceptible to sagging under high moisture loads and does not require increased drying times
- 35 during processing.

SUMMARY

- 40 **[0007]** The present invention encompasses both a method and composition for providing a two-part polymer binder additive for a fibrous sheet for improving both its strength and durability. The two-part polymer binder may be added to augment current organic binders to increase such desirable board properties as strength and durability or the polymers may be added to reduce the amount of organic binder required. Additionally, the polymers may be added in place of conventional organic binders or added in addition to organic binders to improve sag resistance and fibrous sheet performance.
- 45 **[0008]** The two-part polymer binder comprises both the addition of an anionic polymer having a negative charge of between about 4 to about 12 milliequivalents per gram and a cationic polymer having a positive charge of between about 6 to about 12 milliequivalents per gram. The two-part polymer binder forms an interpolyelectrolyte complex.
- 50 **[0009]** In greater detail, the two oppositely charged polymers act together to provide a synergistic effect that when added in addition with an organic binder, the strength and performance of the fibrous sheet is enhanced. The two oppositely charged polymers can coat and bond the organic binder to the fibers of the fibrous sheet to impart strength to the board.
- [0010]** Additionally, a surfactant may be added to the polymer binder. In a further embodiment a hydrogel and/or a latex may also be added. Combinations of all the described embodiments may also be used for the polymer binder.
- 55 **[0011]** The method of forming an enhanced fibrous sheet includes the steps of forming a fibrous slurry and mixing into the fibrous slurry an anionic polymer having a negative charge of between about 4 to about 12 milliequivalents per gram and then mixing a cationic polymer having a positive charge of between about 6 to about 12 milliequivalents per gram. The fibrous sheet is then dried to form the finished product.
- [0012]** Additionally, a fibrous sheet is provided comprising at least one type of fiber and an organic binder. The fibrous

sheet also contains an anionic polymer having a negative charge of between about 4 to about 12 milliequivalents per gram and a cationic polymer having a positive charge of between about 6 to about 12 milliequivalents per gram.

BRIEF DESCRIPTION OF THE DRAWINGS

[0013] In the drawings:

Figure 1 is a schematic presentation of the interpolyelectrolyte complex;

Figure 2 is a schematic presentation of the interpolyelectrolyte complex having cross-linking and formed around a spacer such as a polysaccharide, hydrogel, and latex;

Figure 3 is a schematic presentation of the interpolyelectrolyte complex combined with a surfactant;

Figure 4 is a graphical representation of the binding strength of starch binder and various IPEC combinations having a synergistic effect as shown between IPEC and starch;

Figure 5 is a graphical representation of the binding strength of starch binder and various cross-linked IPEC combinations with a synergistic effect;

Figure 6 is a graphical representation of the binding strength of starch binder and various polyelectrolyte-surfactant complexes (PESCs); and

Figure 7 is a graphical representation of the wet binding strength of starch binder and various PESC combinations having a synergistic effect.

DETAILED DESCRIPTION

[0014] The present invention includes both a method and composition for a two-part polymer binder additive used in fibrous sheet formation for improving both sheet strength and durability. The two-part polymer binder additive comprises a polyanion and polycation to form an interpolyelectrolyte complex (IPEC). The formed IPEC results from various ratios of polyanion to polycation. The polyanion typically consists of a charged portion and a reactive portion. The polycation is usually 100% charged and is added such that its charged portion approximately matches the charged portion of the polyanion. The polyanion is typically added to the board components before the polycation since most board components are anionic.

[0015] The two oppositely charged polymers act together to provide a synergistic effect that when added with an organic binder, the strength and performance of the fibrous sheet is enhanced. The two oppositely charged polymers can coat and bond the organic binder to the fibers of the fibrous sheet to impart strength to the sheet. The organic binder typically used in the formation of fibrous sheets is a polysaccharide. Starch is a commonly used binder due to its economics of use. Additionally, other binders, fillers or spacers may also be used either alone or in combination with each other. For example, a hydrogel or a latex may be used.

[0016] In greater detail, the polyanion is ionic and typically has a negative charge between about 4 and 12 milliequivalents per gram. Its molecular size may be between about 10,000 and 900,000 grams/mole. Depending on the specific molecule, this represents a degree of polymerization of about 100 to 13000 repeat units per polymer molecule. Additionally, the polyanion may be crosslinked to provide further strength. Typically the cross-link density is about 1 per 100 units, however, from zero cross linking to about 1 per 50 units is effective.

[0017] The polycation is also ionic and may have a positive charge from about 6 to 12 milliequivalents per gram. Similarly, its size is also between about 10,000 and 900,000 grams per mole, representing a degree of polymerization of about 50 to 10,000 depending on the particular molecule.

[0018] In weakly acidic polyanions, this may be achieved by partially neutralizing a weak polyacid such as polyacrylic acid or by adding the salt of the acid, such as sodium polyacrylate. For this molecule, the neutralized portion is negatively charged and the unneutralized acid portion can react with starch and paper at the drying temperatures given above. Thus, the charge ratio of polyanion to polycation is typically in the ratio of 1:1.

[0019] For subsequent reactions, normally there exist excess functional groups, groups not involved in the complex formation, to be able to react with some of the board components to form hydrogen or more preferable covalent bonds. Therefore, there is an additional ratio requirement to forming an effective IPEC binder. The ratio of total polyanion acid groups, both neutralized and unneutralized, to total polycation groups is considered. This ratio should typically be between 10:1 and 1.1:1, and is effective at 3:1.

[0020] The polyanion may be selected from the group of polyanions set forth in Table 1 below. The group of listed polyanions is not intended to be exclusive and other polyanions meeting the above described criteria may also be used. For example, block and graft copolymers of the listed polymers having nonionic polymers which are either soluble or water insoluble, but form stable aqueous dispersions, may also be used as one component of the IPEC.

Table 1

Polyanions			
Polycarboxylates	Polyphosphates	Polysulfonates	Polysulfates
Poly (acrylic acid) and its salts (PAA)	Polymetaphosphoric acid and its salts.	Polystyrenesulfonic acid and its salts.	Polyvinylsulfate acid and its salts.
Poly (methacrylic acid) and its salts.	Polyvinylphosphonic acid and its salts.	Lignosulfonic acid and its salts.	Chondroitinsulfate acid and its salts.
Carboxymethylcellulose and its salts		Polyacrylamidalkylpropanesulfonic acid and its salts.	
Polymaleic acid and its salts		Random copolymers of acrylamidalkylpropanesulfonic acid with acrylamide and other hydrophilic and hydrophobic comonomers and their salts.	
Random copolymers of acrylic and/or methacrylic acid with acrylamide and other hydrophilic monomers including those with functional groups reactive with cellulose and/or starch and hydrophobic comonomers and their salts.			
Hydrolyzed copolymers of maleic anhydride with styrene and other hydrophilic and hydrophobic comonomers and their salts.			

[0021] The polycation may be selected from the group of polyanions set forth in Table 2 below. The group of listed polyanions is not intended to be exclusive and other polyanions meeting the above described criteria may also be used. For example, block and graft copolymers of the listed polymers having nonionic polymers which are either soluble or water insoluble, but form stable aqueous dispersions, may also be used as one component of the IPEC.

Table 2

Polycations				
Polymeric Primary amines	Polymeric secondary amines	Polymeric tertiary amines	Polymeric Quaternary amines	Polymeric amines with different amino groups
Polyvinylamine and its salts	Linear polyethyleneimine and its salts.	Poly-N, N-dimethylaminoethyl-methacrylate (PDMAEM) and its salts.	Poly-N, N-diallyl-N, N-dimethylammonium hydroxide (PDADMAH) and its salts.	Branched polyethyleneimine and its salts.

Table 2 (continued)

Polycations				
Polymeric Primary amines	Polymeric secondary amines	Polymeric tertiary amines	Polymeric Quaternary amines	Polymeric amines with different amino groups
Chitosane and its salts.	Linear polypropyleneimine and its salts.	Poly-4-vinylpyridine and its salts.	loenenes hydroxides and their salts.	Partially quarternized poly-4-vinylpyridine and its salts.
		Copolymers of DMAEM with acrylamide and other hydrophilic and hydrophobic comonomers and their salts.	Poly-N-alkyl-4vinylpyridinium salts.	

[0022] The polyanion may be added first with the board components, then the polycation may be added. This may be due to the improved distribution of the resulting IPEC among the board components when the polyanion is added first. Generally, the idea is to add whichever component of the IPEC that is not reactive first. The second component then reacts and locks the IPEC into place evenly among the components. Therefore, since the components used in this example are anionic, one would add the polyanion first. If, however, the components were cationic, then the polycation would be added first. The two-part polymer binder may be added to augment current organic binders to increase such desirable board properties as strength and durability, or the polymers may be added to reduce the amount of organic binder required. Additionally, the polymers may be added in place of conventional organic binders, or added in addition to organic binders to improve sag resistance and fibrous sheet performance.

[0023] Additionally, a surfactant may be added to the polymer binder. The addition of a surfactant creates a polyelectrolyte-surfactant complex (PESC). PESCs are the products of interaction of oppositely charged polyelectrolytes and surfactants. The formation of PESC involves most any pairs of polyanions and cationic surfactants as well as pairs of polycations and anionic surfactants, which form upon mixing an aqueous solution of insoluble products.

[0024] The surfactants may be anionic or cationic. Anionic surfactants include alkylcarboxylic acids and their salts, alkylsulfonic acids and their salts, alkylsulfates, alkylphosphoric acids and their salts, and combinations thereof. Cationic surfactants can include alkylamines, fatty amines, including primary, secondary, tertiary, quaternary amines. This list is not inclusive and other substitutes having similar characteristics are contemplated.

[0025] The method of forming an enhanced fibrous sheet includes the steps of forming a fibrous slurry and mixing into the fibrous slurry an anionic polymer having a negative charge of between about 4 to about 12 milliequivalents per gram and a cationic polymer having a positive charge of between about 6 to about 12 milliequivalents per gram. The fibrous sheet is then dried to form the finished product.

[0026] In greater detail, the process for creating the enhanced fibrous sheet includes forming a fibrous slurry comprised of cellulose and water. Typically, the cellulose is derived from paper, usually in the form of newsprint, which is then pulped in water at a consistency of about 3 to 5% by weight. Of course the consistency may vary depending upon the desired board characteristics. Additionally, other fibers, such as mineral wool, may be added to the slurry. In addition to the fibers, fillers may be added. Example fillers include perlite and clays that can be combined with the paper and water. The total consistency typically is about 3% by weight. Other consistencies ranging from as high as 50% to as low as 1% are also contemplated depending upon the type of board and manufacturing process.

[0027] An organic binder such as starch may also be included into the slurry. The board may be formed without the addition of an organic binder, but the combination of starch and IPEC polymers has been found to create a synergistic effect of enhanced properties. Starch is the most typical binder given that the organic binder is relatively inexpensive when compared to other binders having similar characteristics. Of course, other binders may be used instead of, or in combination with, starch. For example, latex may be used in combination with the starch binder or as a substitution.

[0028] The IPEC is typically added to the above slurry after the organic binder has been mixed into the cellulose slurry. This combination is then mixed. The polyanion is preferably mixed in first, since it will not interact strongly with the other components of the mix because they are also anionically charged. Of course, if the components of the mix were cationically charged, this would not be the case. The addition of the polyanionic portion of the IPEC first aids in distributing polyanion evenly among the components. It is contemplated that the IPEC components may be added

simultaneously, in reserve order or premixed, so long as the IPEC is formed in the fibrous mix.

[0029] The polycationic portion of the IPEC may then be added after the addition of the polyanionic portion. The IPEC reaction may then occur, causing polyanionic and polycationic polymers to form a complex and become entangled and absorbed onto the board components, especially the starch and cellulosic fibers.

[0030] The resulting slurry may then be formed into boards using typical board and papermaking techniques. For example, a high molecular weight flocculant polymer may be added to aid in drainage to speed up the drying process. The slurry is typically pumped onto a fourdrinier machine, the water drained by gravity, then by vacuum, and finally the structure is pressed to a constant thickness.

[0031] The formed sheet may then be dried and cut. Drying may occur in ovens. The final product is typically sanded and decorated by surface treatment and painting.

[0032] The invention will be more easily understood by referring to the examples of the invention and the control examples that follow. The following examples are given for illustrative purposes and are not to be understood as limiting the present invention.

IPEC Examples

Example 1

[0033] 4.5g of mineral wool were dispersed in 400 ml warm ($T=40^{\circ}\text{C}$) 0.001N KCl aqueous solution under stirring by a mechanical stirrer. Then 1.8g of corn starch and 17.1g of perlite were added. Newsprint (6.6g) was kept in 200ml warm ($T=40^{\circ}\text{C}$) water for 1 hour, ground by blender and mixed with the other components of composition under stirring. The total volume of mixture was made to 1000 ml.

[0034] Interpolyelectrolyte complex (IPEC) based on partially neutralized poly(acrylic acid) (PAA) with poly(N,N-dimethyl-N,N-diallylammonium chloride) (PDADMAC) was used as a starch modifier. To make this complex, 3.6ml 0.1N aqueous solution of sodium poly(acrylate) (NaPA) (0.034g of NaPA) and 7.2 ml 0.1N aqueous solution of PAA (0.052g of PAA) were added to the mixture under stirring. After that, 3.6ml 0.1N aqueous solution of poly(N,N-dimethyl-N,N-diallylammonium chloride) (PDADMAC) (0.058g of PDADMAC) was added under stirring for about 2 minutes. Thus, 0.145g of IPEC(PAA-PDADMAC), $\Phi = [\text{carboxylic groups}]/[\text{amine groups}] = 3.0$ was added to the composition as a modifier. Flocculant (0.0188) in the form of 0.2wt.% aqueous dispersion was added by plastic syringe.

[0035] The obtained mixture was filtered with a Buchner funnel using 2 layers of paper filter and dried in the "starch-brewing" regime. To create the brewed starch regime, the sample was enveloped in aluminum foil and kept at 177°C for 1 hour. After that it was unwrapped and dried again at 177°C for 1 hour.

[0036] The compositions were tested in dry and wet states by bending using Instron 1195(UK) or UTS-10 (Germany) dynamometers. The samples were cut into strips 10mm by 80-120mm. The thickness of each strip was estimated using an optimizer. The wet composition samples were prepared via equilibration with water vapor at 95% relative humidity (95RH) (saturated solution of KNO_3 in distilled water at 20°C) in a dessicator for 14 days. All the mechanical tests were carried out just after taking the samples out of the dessicator. The rate of deformation was 5mm/min. The values of stress at break, σ^* (N/mm² or MPa) were estimated from stress-strain curves. The results of mechanical testing were:

$\sigma^* = 0.45\text{MPa}$, dry state

$\sigma^* = 0.15\text{MPa}$, wet state

(σ^* -value for composition not containing IPEC, prepared in the "starch-brewing" regime)

$\sigma^* = 0.35\text{MPa}$, dry state

$\sigma^* = 0.10\text{MPa}$, wet state).

Example 2

[0037] The IPEC modified composition was prepared as for Example 1, except that 0.3g IPEC(PAA-PDADMAC), Φ was added as a modifier. 7.2ml 0.1N aqueous solution of sodium poly(acrylate) (NaPA) (0.07g of NaPA), 14.4ml 0.1N aqueous solution of PAA (0.10g of PAA) and 7.2ml 0.1N aqueous solution of poly(N,N-dimethyl-N,N-diallylammonium chloride) (PDADMAC) (0.12g of PDADMAC) were added to the composition under stirring. 0.018g of flocculant in the form of 0.2wt.% aqueous dispersion was added last.

[0038] The results of mechanical testing:

$\sigma^* = 0.50\text{MPa}$, dry state

$\sigma^* = 0.20\text{MPa}$, wet state.

Example 3

[0039] The IPEC modified composition was prepared as for Example 1, except that the 0.9g of starch was added

instead of 1.8g.

[0040] The results of mechanical testing:

$\sigma^*=0.38\text{MPa}$, dry state

$\sigma^*=0.10\text{MPa}$, wet state

(σ^* -value for composition including 0.9g of starch and not containing IPEC

$\sigma^*=0.20\text{MPa}$, dry state

$\sigma^*=0.05\text{MPa}$, wet state).

Example 4

[0041] The IPEC modified composition was prepared as for Example 2, except that the composition included 0.9g of starch instead of 1.8g.

[0042] The results of mechanical testing:

$\sigma^*=0.50\text{MPa}$, dry state

$\sigma^*=0.25\text{MPa}$, wet state.

Example 5

[0043] The IPEC modified composition was prepared as for Example 1, except that the composition included 0.9g of starch and 0.48g IPEC(PAA-PDADMAC), Φ as a modifier. 12ml 0.1N aqueous solution of sodium poly(acrylate) (NaPA) (0.11g of NaPA), 24ml 0.1N aqueous solution of PAA (0.173g of PAA) and 12ml 0.1N aqueous solution of poly(N,N-dimethyl-N,N-diallylammonium chloride) (PDADMAC) (0.194g of PDADMAC) were added under stirring. 0.018g of flocculant in the form of 0.2wt.% aqueous dispersion was added last.

[0044] The results of mechanical testing:

$\sigma^*=0.60\text{MPa}$, dry state

$\sigma^*=0.30\text{MPa}$, wet state.

Example 6

[0045] The IPEC modified composition was prepared as for Example 1, except that the composition did not contain starch and 1.8g IPEC(PAA-PDADMAC), Φ was added as a modifier. 44.0 ml. 0.1N aqueous solution of sodium poly(acrylate) (NaPA) (0.42g of NaPA), 88.0 ml 0.1N aqueous solution of PAA (0.63g of PAA) and 44.0 ml 0.1N aqueous solution of poly(N,N-dimethyl-N,N-diallylammonium chloride) (PDADMAC) (0.71g of PDADMAC) were added to the composition under stirring. 0.018g of flocculant in the form of 0.2wt.% aqueous dispersion was added last.

[0046] The results of mechanical testing:

$\sigma^*=0.70\text{MPa}$, dry state

$\sigma^*=0.40\text{MPa}$, wet state.

[0047] The results of mechanical testing of the compositions in terms of the values of stress at break (MPa) are listed in Table 3 and Figure 4. Figure 4 and Table 3 illustrate the effects of starch and IPEC modifier compared to starch alone and IPEC alone, on the mechanical characteristics of the composition prepared in the "brewing regime."

Table 3

IPEC Data					
	Starch (g)	IPEC (g)	Total binder (g)	Stress at break σ^* dry (Mpa)	Stress at break σ^* wet (Mpa)
Control 1 IPEC alone	0	0.5	0.5	0.4	0.3
	0	0.9	0.9	0.5	0.35
	0	1.2	1.2	0.6	0.4
	0	1.8	1.8	0.7	0.4
	0	2.7	2.7	0.85	0.45
Control 2 Starch alone	0.5	0	0.5	0.15	0.1
	0.9	0	0.9	0.2	0.05
	1.2	0	1.2	0.25	0.07
	1.8	0	1.8	0.35	0.1
	2.7	0	2.7	0.55	0.25
Combination 0.5 g Starch plus varied IPEC	0.5	0.3	0.8	0.5	3
	0.5	0.5	1	0.65	0.4
	0.5	0.9	1.4	0.7	0.4
Combination 0.9 g Starch plus varied IPEC	0.9	0.15	1.05	0.38	0.1
	0.9	0.3	1.2	0.5	0.25
	0.9	0.5	1.4	0.6	0.3
Combination 1.2 g Starch plus varied IPEC	1.2	0.3	1.5	0.5	0.25
	1.2	0.5	1.7	0.6	0.3
	1.2	0.9	2.1	0.7	0.35
Combination 1.8 g Starch plus varied IPEC	1.8	0.15	1.95	0.45	0.15
	1.8	0.3	2.1	0.5	0.2
	1.8	0.5	2.3	0.6	0.25

PESC (Surfactant) Examples

[0048] In the following examples, polyelectrolyte-surfactant complexes (PESC) additives were added to a basic mix of fiberboard components. The mechanical characteristics of the compositions containing different amounts of starch and PESC additives are illustrated in the examples. The basic components for the fiberboard were prepared in the brewing regime and were added in the following amounts:

Newsprint	6.6g
Mineral Wool	4.5g
Perlite	17.1g
Starch	0-2.7g

(continued)

Flocculant	0.018g
0.001 N KCl aqueous solution	1000g

Example 7

[0049] Mineral wool, starch, perlite and newspaper were mixed as described in Example 1. Polyelectrolyte-surfactant complex (PESC) formed by partially neutralized poly(acrylic acid) (PAA) and dodecyltrimethylammonium bromide (DDTMAB) was used as a modifier. 3.6ml 0.1N aqueous solution of sodium poly(acrylate) (NaPA) (0.034g of NaPA) and 7.2ml 0.1N aqueous solution of PAA (0.052g of PAA) were added under stirring. 9.0 ml 0.04N aqueous solution of DDTMAB (0.11g) was added and stirred for 2 minutes. Thus, 0.2g of PESC(PAA-DDTMAB), Φ =[carboxylic groups]/[amine groups]=3.0 was added to the composition as a modifier. 0.018g of flocculant in the form of 0.2wt.% aqueous dispersion was added last by a plastic syringe.

[0050] The mixture was filtered with a Buchner funnel and dried in the "starch-brewing" regime as described in Example 1.

[0051] The results of mechanical testing:

$\sigma^*=0.50\text{MPa}$, dry state

$\sigma^*=0.30\text{MPa}$, wet state.

Example 8

[0052] The PESC modified composition was prepared as described in Example 7, except that DDTMAB was added first.

[0053] The results of mechanical testing:

$\sigma^*=0.47\text{MPa}$, dry state

$\sigma^*=0.29\text{MPa}$, wet state.

Example 9

[0054] The PESC modified composition was prepared as described in Example 7, except that 0.144g of PESC (PAA-DDTMAB), Φ =[carboxylic groups]/[amine groups]=1.0, was added as a modifier. 3.6ml 0.1N aqueous solution of sodium poly(acrylate) (NaPA) (0.034g of NaPA) and after that, 9.0 ml 0.04N aqueous solution of DDTMAB (0.11g) was added under stirring.

[0055] The results of mechanical testing:

$\sigma^*=0.50\text{MPa}$, dry state

$\sigma^*=0.30\text{MPa}$, wet state.

Example 10

[0056] In this example the PESC was added without the addition of starch. The stoichiometric complex formed by sodium polyacrylate (NaPA) and dodecyltrimethylammonium bromide (DDTMAB) named as PESC, $\phi=1$, as well as the nonstoichiometric PESC, $\phi=3.0$ containing a threefold excess of poly(acrylic acid), were used.

[0057] Newsprint, mineral wool and perlite were mixed in 1000 ml of warm (40° C) 0.001 N KCl aqueous solution under stirring. Then, 0.1 N NaPA aqueous solution and the corresponding amount of 0.04 N aqueous solution of DDTMAB were added under stirring for about 2-3 minutes. In the case of PESC, $\phi=1$ the equimolar amounts of NaPA and DDTMAB were added. In the case of PESC, $\phi=3.0$, the predetermined amount of 0.1 N aqueous solution of partially (one third) neutralized poly(acrylic acid), and corresponding amount of DDTMAB were consequently added under stirring for about 2-3 minutes. The flocculant in the form of 0.2 wt.% aqueous solution was added last by means of quick injecting it by plastic syringe.

[0058] The obtained mixtures were filtered with a Buchner funnel. The samples were enveloped in aluminum foil and kept at 177° C for 1 hour and unwrapped and dried at 177° C for 1 hour.

[0059] The wet compositions were prepared via equilibration with water vapor at 95% relative humidity (95 RH) saturated solution of KNO_3 in distilled water at 20° C) in the dessicator for 14 days. The samples were taken out the dessicator and were cut into 5-6 strips in the form of parallelepipeds with the length 100 mm, the width 10 mm and the thickness 8-10 mm. These strips were kept at 95 RH for 24 hours. All the mechanical tests were carried out just after taking the strips out the dessicator using UTS-10 dynamometer (Germany) with the gauge length 70 mm.

[0060] The results of mechanical testing of the compositions in terms of the values of stress — at break, σ^* (MPa) are listed in the Table 4, control 1 and control 2 sections. Table 4 illustrates the effects of PESC (PAA-DDTMAB) $\varphi=1$, $\varphi=3.0$ ($\varphi=[\text{PAA}]/[\text{DDTMAB}]$) as binders on the mechanical characteristics of the composition prepared in the "brewing regime." All samples contain 6.6 g of newsprint, 4.5 g of mineral wool, 17.1 g of perlite and 0.018 g of flocculant. The samples did not contain starch. The samples were tested in dry and wet state.

[0061] The strengthening effect of PESC, $\varphi=1$ and PESC, $\varphi=3.0$ used as co-binders together with the starch was also tested. The procedure of the preparation of the composition was the same as described above; however, the only difference is the variable amount of the starch. The samples for mechanical testing were prepared in the "starch brewing" regimes and were tested in the dry as well as in the wet state.

[0062] The results of mechanical testing of compositions containing the starch binder and PESC, $\varphi=1$ or PESC, $\varphi=3.0$ co-binders are listed in Table 4 under combinations. Table 4 and Figures 5 and 6 illustrate the joint action of starch binder and PESC (PAA-DDTMAB) $\varphi=1$, $\varphi=3.0$ co-binder on the mechanical characteristics of the compositions prepared in the brewing regime. All samples contained 6.6 g of newsprint, 4.5 g of mineral wool, 17.1 g of perlite and 0.018 g of flocculant. The samples were tested in dry and wet state.

Table 4

Polyelectrolyte-Surfactant Complexes (PESC) Data					
	Starch (g)	PESC (g)	Total binder (g)	Stress at break σ^* dry (Mpa)	Stress at break σ^* wet (Mpa)
Control 1 PESC (1:1) alone	0	0.9	0.9	0.25	0.1
	0	1.2	1.2	0.1	0.1
	0	1.8	1.8	0.15	0.1
	0	2.7	2.7	0.3	0.3
Control 2 PESC (3:1) alone	0	0.9	0.9	0.2	0.1
	0	1.2	1.2	0.25	0.1
	0	1.8	1.8	0.5	0.35
	0	2.7	2.7	0.55	0.5
Control 3 Starch alone (same data as in Table 3)	0.5	0	0.5	0.15	0.1
	0.9	0	0.9	0.2	0.05
	1.2	0	1.2	0.25	0.07
	1.8	0	1.8	0.35	0.1
	2.7	0	2.7	0.55	0.25
Combination 0.9 g Starch plus varied PESC (1:1)	0.9	0.15	1.05	0.2	0.15
	0.9	0.3	1.2	0.3	0.15
	0.9	0.5	1.4	0.25	0.15
	0.9	0.9	1.8	0.2	0.2
Combination 0.9 g Starch plus varied PESC (3:1)	0.9	0.15	1.05	0.2	0.2
	0.9	0.3	1.2	0.4	0.2
	0.9	0.9	1.8	0.35	0.3
	0.9	0.5	1.4		0.25
Combination 1.8 g Starch plus varied PESC (1:1)	1.8	0.15	1.95	0.4	0.2
	1.8	0.3	2.1	0.5	0.25
	1.8	0.5	2.3	0.6	0.25
Combination 1.8g Starch plus varied PESC (3:1)	1.8	0.15	1.95	0.5	0.3
	1.8	0.3	2.1	0.6	0.25
	1.8	0.5	2.3	0.8	0.3
	1.8	0.9	2.7	0.6	0.3

The strengthening effect of mixed IPEC+PESC co-binder in "starch brewing" regime was also tested. Non-stoichiometric mixed IPEC (PAA-PDADMAC) + PESC (PAA-DDTMAB), $\phi=3.0$ was used. It was prepared as follows:

The predetermined amount of 0.1 N aqueous solution of partially neutralized ($\alpha=0.33$) poly(acrylic acid) and then corresponding amount of 0.04 N aqueous solution of the equimolar mixture of PDADMAC and DDTMAB were

added under stirring for about 2-3 minutes.

[0065] The compositions containing 0.9 g of the starch binder and different additives of mixed (IPEC+PESC), $\varphi=3.0$ co-binder were tested mechanically in the dry and wet state. The results of the latest measurements are listed in Table 3. Table 3 illustrates the joint action of starch binder and mixed IPEC (PAA-PDADMAC) + PESC (PAA-DDTMAB), $\varphi=3.0$ ($\varphi=[\text{PAA}]/[\text{DDTMAB}+\text{PDADMAC}]$ at $[\text{DDTMAB}]=[\text{PDADMAC}]$) co-binder on the mechanical characteristics of the compositions prepared in the "brewing" regime. All samples contained 6.6 g of newsprint, 4.5 g of mineral wool, 17.1 g of perlite and 0.018 g of flocculant. The samples were tested in dry and wet state.

Table 5

IPEC and PESC Combinations as Starch Modifiers				
No.	Amount of starch, g	Amount of IPEC+PESC, $\varphi=3.0$	Sample state	σ^* , MPa
1	0.9	0	dry	0.2
			wet	0.1
2	0.9	0.15	dry	0.3 (0.5)
			wet	0.2
3	0.9	0.3	dry	0.35 (0.6)
			wet	0.2
4	0.9	0.5	dry	0.4 (0.7)
			wet	0.2
5	0.9	0.9	dry	0.4
			wet	0.2

Cross-linked Interpolyelectrolyte Complexes (#IPEC)

[0066] In the following examples, the effect of slightly cross-linked polyelectrolyte and linear polyelectrolyte on the mechanical characteristics of the compositions is illustrated. We used the commercial microgel of slightly cross-linked highly water swollen technical poly(acrylic acid) "Carbopol" 2001. The procedure of preparation of gel sample was the following: The predetermined amount of the dry "Carbopol" was swollen in 300 ml of tap water for five minutes. Then the calculated amount of 0.1N aqueous NaOH was added to neutralize the $-\text{COOH}$ groups of "Carbopol" up to the degree of neutralization $\alpha=0.33$ (the amount of NaOH added was equal to 33% relative to the $-\text{COOH}$ groups of "Carbopol." The partially neutralized "Carbopol" was additionally swollen in water for 12 hours. The equilibrium degree of swelling, defined as the ratio of the mass of swollen gel to that of the dry gel equaled 1000. The size of the equilibrium swollen microgel particles was about 1 mm.

[0067] The standard procedure of preparation of the composition was used: Newsprint (6.6g), mineral wool (4.5g), perlite (17.1g), and starch (0-18g) were mixed in 500 ml of warm (40°C) 0.002N KCl aqueous solution under stirring. Then 300 ml of partially neutralized "Carbopol" microgel, prepared in advance, was added to the mixture under stirring. Then the predetermined amount of 0.1N aqueous solution of PDADMAC was added to make the ratio of total carboxylic groups to ammonium groups equal to 3.0. Since the carboxylic groups were previously one third neutralized, the ratio of neutralized carboxylic groups to ammonium groups thus equals 1.0. Again, an additional amount of water was added to make the total volume equal to 1000 ml. Then 0.018g of flocculant was added last. The mixtures were filtered and prepared in the "brewing regime" as usual. The results of the mechanical testing of the samples are presented in Table 6 and Figure 7.

Table 6

Cross-linked (#) IPEC Data					
	Starch (g)	#IPEC (g)	Total binder (g)	Stress at break σ^* dry (Mpa)	Stress at break σ^* wet (Mpa)
Control 1 #IPEC alone	0	0.075	0.075	0.25	0.15
	0	0.3	0.3	0.25	0.15
	0	0.5	0.5	0.25	0.15
	0	0.9	0.9	0.12	0.07
Control 2 Starch alone (same data as in Table 3)	0.5	0	0.5	0.15	0.1
	0.9	0	0.9	0.2	0.05
	1.2	0	1.2	0.25	0.07
	1.8	0	1.8	0.35	0.1
	2.7	0	2.7	0.55	0.25
Combination 0.5 g Starch plus varied #IPEC	0.5	0.15	0.65	0.25	0.2
	0.5	0.3	0.8	0.35	0.2
	0.5	0.5	1	0.35	0.2
	0.5	0.9	1.4	0.4	0.2
Combination 0.9 g Starch plus varied #IPEC	0.9	0.075	0.975	0.5	0.2
	0.9	0.15	1.05	0.55	0.3
	0.9	0.3	1.2	0.4	0.3
Combination 1.2 g Starch plus varied #IPEC	1.2	0.075	1.275	0.6	0.35
	1.2	0.15	1.35	0.5	0.4
	1.2	0.3	1.5	0.4	0.3
Combination 1.8 g Starch plus varied #IPEC	1.8	0.075	1.875	0.8	0.5
	1.8	0.15	1.95	0.7	0.4
	1.8	0.3	2.1	0.45	0.3

[0068] While Applicants have set forth embodiments as illustrated and described above, it is recognized that variations may be made with respect to disclosed embodiments. Therefore, while the invention has been disclosed in various forms only, it will be obvious to those skilled in the art that many additions, deletions and modifications can be made without departing from the spirit and scope of this invention, and no undue limits should be imposed except as set forth in the following claims.

Claims

1. A polymer binder for a fibrous sheet comprising:


an anionic polymer having a negative charge of between about 4 to about 12 milliequivalents per gram; and

a cationic polymer having a positive charge of between about 6 to about 12 milliequivalents per gram.

2. The binder of claim 1, wherein the molar ratio of total polyanion acid groups to total polycation groups is between about 10:1 to about 1.1:1.
3. The binder of claim 2, wherein the molar ratio of anionic polymer to cationic polymer is about 3:1.
4. The binder of claim 1, wherein the molecular size of the anionic polymer is between about 10,000 to about 900,000 grams per mole.
5. The binder of claim 1, wherein the anionic polymer is crosslinked.
6. The binder of claim 5, wherein the anionic polymer has a crosslinked density of up to about 1 per 50 units.
7. The binder of claim 1, wherein the molecular size of the cationic polymer is between about 10,000 to about 900,000 grams per mole.
8. The binder of claim 1, wherein the binder forms an interpolyelectrolyte complex.
9. The binder of claim 1, further including a spacer selected from the group consisting of a polysaccharide, a hydrogel, a latex and combinations thereof.
10. The binder of claim 9, wherein the polysaccharide comprises starch.
11. The binder of claim 1, further including a surfactant.
12. The binder of claim 11, wherein the surfactant is selected from the group consisting of alkylamines, fatty amines and combinations thereof.
13. The binder of claim 1, wherein anionic polymer to cationic polymer charge ratio is about 1:1.
14. The binder of claim 1, wherein the anionic polymer is selected from the group consisting of polycarbohydrates, polyphosphates, polysulfonates, polysulfates and combinations thereof.
15. The binder of claim 1, wherein the cationic polymer is selected from the group consisting of polymeric amine.
16. The binder of claim 15, wherein the polymeric amine is selected from the group consisting of primary amines, secondary amines, tertiary amines, quaternary amines and combinations thereof.
17. The binder of claim 1, wherein the anionic polymer is weakly acidic.
18. A method of forming a fibrous sheet comprising:
 - forming a fibrous slurry;
 - mixing into the fibrous slurry an anionic polymer having a negative charge of between about 4 to about 12 milliequivalents per gram;
 - mixing into the fibrous slurry a cationic polymer having a positive charge of between about 6 to about 12 milliequivalents per gram; and
 - drying the fibrous sheet to form the fibrous sheet.
19. The method of claim 18, wherein the molar ratio of total polyanion acid groups to total polycation groups is between about 10:1 to about 1.1:1.
20. The method of claim 19, wherein the molar ratio of anionic polymer to cationic polymer is about 3:1.
21. The method of claim 18, wherein the molecular size of the anionic polymer is between about 10,000 to about 900,000 grams per mole.

22. The method of claim 18, wherein the molecular size of the cationic polymer is between about 10,000 to about 900,000 grams per mole.
23. The method of claim 18, wherein the binder forms an interpolyelectrolyte complex.
24. The method of claim 18, further including a polysaccharide.
25. The method of claim 24, wherein the polysaccharide comprises starch.
26. The method of claim 18, wherein anionic polymer to cationic polymer charge ratio is about 1:1.
27. The method of claim 18, wherein the anionic polymer is selected from the group consisting of polycarbohydrates, polyphosphates, polysulfonates, polysulfates and combinations thereof.
28. The method of claim 18, wherein the cationic polymer is selected from the group consisting of polymeric amine.
29. The method of claim 28, wherein the polymeric amine is selected from the group consisting of primary amines, secondary amines, tertiary amines, quaternary amines and combinations thereof.
30. The method of claim 18, wherein the anionic polymer is weakly acidic.
31. A fibrous sheet comprising:
 - at least one type of fiber;
 - an anionic polymer having a negative charge of between about 4 to about 12 milliequivalents per gram; and
 - a cationic polymer having a positive charge of between about 6 to about 12 milliequivalents per gram.
32. The fibrous sheet of claim 31, wherein the molar ratio of total polyanion acid groups to total polycation groups is between about 10:1 to about 1.1:1.
33. The fibrous sheet of claim 32, wherein the molar ratio of anionic polymer to cationic polymer is about 3:1.
34. The fibrous sheet of claim 31, wherein the molecular size of the anionic polymer is between about 10,000 to about 900,000 grams per mole.
35. The fibrous sheet of claim 31, wherein the molecular size of the cationic polymer is between about 10,000 to about 900,000 grams per mole.
36. The fibrous sheet of claim 31, wherein the binder forms an interpolyelectrolyte complex.
37. The fibrous sheet of claim 31, further including a polysaccharide.
38. The fibrous sheet of claim 37, wherein the polysaccharide comprises starch.
39. The fibrous sheet of claim 31, wherein anionic polymer to cationic polymer charge ratio is about 1:1.
40. The fibrous sheet of claim 31, wherein the anionic polymer is selected from the group consisting of polycarbohydrates, polyphosphates, polysulfonates, polysulfates and combinations thereof.
41. The fibrous sheet of claim 31, wherein the cationic polymer is selected from the group consisting of polymeric amine.
42. The fibrous sheet of claim 41, wherein the polymeric amine is selected from the group consisting of primary amines, secondary amines, tertiary amines, quaternary amines and combinations thereof.
43. The fibrous sheet of claim 31, wherein the anionic polymer is weakly acidic.

Figure 1.
Interpolyelectrolyte Complex (IPEC)
Dry Strength Enhancement
Polyacrylic acid example



- Neutralized anionic COO^- acid groups, 33:1 to protonated acid groups
- ⊖ Functional COOH acid groups, 3:1 to anionic groups
- ⊕ Cationic polymer, matched 1:1 to anionic groups
- ⊖ Proton from acid group, creating neutralized anionic group.

Figure 2.
IPEC plus Cross-linking and Binder
Wet and Dry Strength
 Functional groups attach to binder at elevated temperature..




Figure 3.
Polyelectrolyte Surfactant Complexes (PESCs)
 Cationic Surfactant with Anionic polymer.
 Wet and Dry Strength




Figure 4
Synergistic Effect of IPEC and Starch on Dry Strength




Figure 5
Synergistic Effect of PESC and Starch on Dry Strength




Figure 6
Synergistic Effect of PESC and Starch on Wet Strength





Figure 7
Synergistic Effect of Cross-linked (#)IPEC and Starch on Dry Strength





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 01 7318

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 5 338 406 A (SMITH DOUGLAS C) 16 August 1994 (1994-08-16) * claims 1-23 *	1-3, 14-16, 18-20, 27-29, 31,32, 40-42	D21H21/18 D21H17/42 D21H17/44
X	EP 0 362 770 A (HERCULES INC) 11 April 1990 (1990-04-11) * claims 1-21 *	1-3, 14-16, 18-20, 27-29, 31,32, 40-42	
X	EP 0 723 047 A (HERCULES INC) 24 July 1996 (1996-07-24) * claims 1-25 *	1-3, 14-16, 18-20, 27-29, 31,32, 40-42	TECHNICAL FIELDS SEARCHED (Int.Cl.7) D21H
X	CA 1 110 019 A (MITSUBISHI CHEM IND;KYORITSU YUKI CO LTD) 6 October 1981 (1981-10-06) * claims 1-14; examples 1-12 * -/--	1-3, 14-16, 18-20, 27-29, 31,32, 40-42	
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 8 October 2002	Examiner Karlsson, L
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03 82 (P&C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 01 7318

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 5 633 300 A (DASGUPTA SUNIL P) 27 May 1997 (1997-05-27) * claims 1-13 *	1-3, 14-16, 18,19, 27-29, 31,32, 40-42	
X	WO 99 05361 A (HERCULES INC) 4 February 1999 (1999-02-04) * claims 1-80; figure 2; examples 1-9 *	1,9,10, 31,37,38	
P, A	WO 01 77437 A (SCA HYGIENE PROD AB ;ANDREASSON BO (SE); SANDBERG SUSSAN (SE)) 18 October 2001 (2001-10-18) * the whole document *	1-43	
A	US 6 235 835 B1 (ETTL ROLAND ET AL) 22 May 2001 (2001-05-22) * the whole document *	9,10,24, 25,37,38	
A	US 5 641 855 A (SCHERR GUENTER ET AL) 24 June 1997 (1997-06-24) * the whole document *	1-43	
A	US 5 134 179 A (FELEGI JR JOHN ET AL) 28 July 1992 (1992-07-28) * the whole document *	1-43	TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 8 October 2002	Examiner Karlsson, L
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.82 (PAC11)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 01 7318

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08-10-2002

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5338406	A	16-08-1994	AT 109230 T	15-08-1994
			AU 619599 B2	30-01-1992
			AU 4252389 A	05-04-1990
			BR 8905018 A	08-05-1990
			DE 68917069 D1	01-09-1994
			DE 68917069 T2	08-12-1994
			EP 0362770 A2	11-04-1990
			ES 2059664 T3	16-11-1994
			FI 894684 A ,B,	04-04-1990
			JP 2251696 A	09-10-1990
			JP 2862913 B2	03-03-1999
			KR 159921 B1	15-01-1999
			RU 2040618 C1	25-07-1995
			ZA 8907516 A	26-09-1990
EP 0362770	A	11-04-1990	AT 109230 T	15-08-1994
			AU 619599 B2	30-01-1992
			AU 4252389 A	05-04-1990
			BR 8905018 A	08-05-1990
			DE 68917069 D1	01-09-1994
			DE 68917069 T2	08-12-1994
			EP 0362770 A2	11-04-1990
			ES 2059664 T3	16-11-1994
			FI 894684 A ,B,	04-04-1990
			JP 2251696 A	09-10-1990
			JP 2862913 B2	03-03-1999
			KR 159921 B1	15-01-1999
			RU 2040618 C1	25-07-1995
			US 5338406 A	16-08-1994
			ZA 8907516 A	26-09-1990
EP 0723047	A	24-07-1996	US 6228217 B1	08-05-2001
			AT 205903 T	15-10-2001
			AU 698805 B2	05-11-1998
			AU 4096596 A	25-07-1996
			BR 9600096 A	27-01-1998
			CA 2167024 A1	14-07-1996
			DE 69615229 D1	25-10-2001
			EP 0723047 A2	24-07-1996
			FI 960135 A	14-07-1996
			JP 8232191 A	10-09-1996
			RU 2150543 C1	10-06-2000
CA 1110019	A	06-10-1981	SE 443818 B	10-03-1986
			CA 1110019 A1	06-10-1981
			SE 7804680 A	25-10-1979

EPO FORM P4559

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 02 01 7318

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08-10-2002

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5633300	A	27-05-1997	US 5502091 A	26-03-1996
			US 5338407 A	16-08-1994
			AT 163699 T	15-03-1998
			AU 659902 B2	01-06-1995
			AU 3107293 A	24-06-1993
			BR 9205156 A	29-06-1993
			CA 2086030 A1	24-06-1993
			DE 69224604 D1	09-04-1998
			DE 69224604 T2	18-06-1998
			EP 0548960 A1	30-06-1993
			JP 3163188 B2	08-05-2001
			JP 6010296 A	18-01-1994
			MX 9207537 A1	01-06-1993
			US 5318669 A	07-06-1994
WO 9905361	A	04-02-1999	US 6294645 B1	25-09-2001
			AU 8511398 A	16-02-1999
			WO 9905361 A1	04-02-1999
			ZA 9806682 A	25-01-1999
WO 0177437	A	18-10-2001	AU 4297101 A	23-10-2001
			SE 0001268 A	07-10-2001
			WO 0177437 A1	18-10-2001
US 6235835	B1	22-05-2001	DE 19701523 A1	23-07-1998
			WO 9831711 A1	23-07-1998
			EP 0952988 A1	03-11-1999
			JP 2001509201 T	10-07-2001
US 5641855	A	24-06-1997	DE 4244194 A1	30-06-1994
			AT 154051 T	15-06-1997
			CA 2145667 A1	07-07-1994
			DE 59306701 D1	10-07-1997
			WO 9414873 A1	07-07-1994
			EP 0675914 A1	11-10-1995
			ES 2102197 T3	16-07-1997
			FI 953134 A	22-06-1995
			JP 8507796 T	20-08-1996
US 5134179	A	28-07-1992	US 4963603 A	16-10-1990
			AT 119508 T	15-03-1995
			AU 4627589 A	26-06-1990
			CA 2003204 A1	25-05-1990
			DE 68921616 D1	13-04-1995
			DE 68921616 T2	13-07-1995
			EP 0406354 A1	09-01-1991

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

THIS PAGE BLANK (USPTO)